

Madison

GalvaClad™ Aromatic

NEW!

GalvaClad™ Aromatic is a 1:1 ratio, 100% solids (i.e. solvent free) polyurethane protective coating for galvanized structures • No elaborate surface preparation such as blasting

Description

As part of a complete coating system with Madison GalvaPrep™, GalvaClad™ Aromatic is ideal for a variety of galvanized structures destined for industrial and commercial applications.

NOTE: When exposed to direct sunlight, GalvaClad™ Aromatic will fade and chalk with time. This does not diminish the anti-corrosive properties of the product. When long term gloss and colour retention is desired, we recommend considering a sister product, GalvaClad™ Aliphatic.

Features

- No surface blasting – simply spray surface with Madison's GalvaPrep™
- Fast setting, targeted at high throughput applications
- Self priming, direct to metal (DTM) application
- High build can be achieved in one continuous multi-pass application
- Excellent resistance to long-term corrosion
- Suitable for both interior and exterior applications (see note below), including embedded service
- Low VOC's (minimal solvents) and low odour
- Application with plural component spray equipment

Application

- Virtually any galvanized structure: beams, girders, building components, power poles, cellular towers
- Any intended end use: atmospheric, embedded or immersion service (including marine)
- Zinc-plated panels and sheets used in roofs, walls, silos
- Galvanized piping
- Any metallized steel product
- Industrial, automotive, pulp/paper, mining, commercial, agricultural, piping, construction, petrochemical, harbours/shipping, food and beverage

Physical and Application Properties

Appearance	<i>Opaque pigmented liquid</i>
% Solids	<i>100%</i>
Application Temperature Range	<i>-40°C (-40°F) to 65°C (150°F)</i>
Cure to Touch (25°C/78°F)	<i>5 min.</i>
Cure to Handle (25°C/78°F)	<i>20 min.</i>
Recoat Time (25°C/78°F)	<i>Up to 45 min.</i>
Cure to Service (25°C/78°F)	<i>24 hrs.</i>
Colors	<i>Brown, Gray, Black, Off White Other colours may be special ordered.</i>



MADISON CHEMICAL INDUSTRIES INC.

490 McGeachie Drive, Milton, ON, Canada L9T 3Y5 Tel: 905-878-8863 Fax: 905-878-1449
Email: sales@madisonchemical.com Web Site: www.madisonchemical.com 03/26/08

