



CORROCOTE II PW

TECHNICAL DATA

POLYURETHANE WATER STORAGE SYSTEM LINING

THE PRODUCT AND ITS USES

CorroCote II PW is a two component, instant setting, 100% solids polyurethane designed to protect potable water, fuel and chemical storage tanks from internal corrosion and abrasion. CorroCote II PW cures to form a tough, durable, non-toxic polyurethane solid that will not impart any taste to the contents of the tank, even at elevated temperatures.

CorroCote II PW can be spray applied at any ambient temperature, in a single multi-pass coat, to any desired thickness. This fast and trouble-free application improves productivity and increases throughput. Having zero VOC's, this coating is also excellent for areas with strict regulations.

CorroCote II PW (AM) This modification contains an EPA-registered Anti-Microbial agent which helps prevent microbiological attack of the coating and the substrate being protected.

APPROVALS AND LISTINGS

NSF International: NSF/ANSI Standard 61 for potable water applications. Rated D.HOT 60°C (140°F)

US Food & Drug Administration: 21 CFR177.1680 for dry food contact



TECHNICAL INFORMATION

PROPERTY	TEST DESCRIPTION	RESULTS
Application Temperatures	N/A	-40°C(-40°F) to 65°C(150°F)
Initial Setting Time	@ 20°C/70°F	3-7 minutes
Curing Time Before Handling	@ 20°C/70°F	8-20 minutes
Curing Time Before Immersion	@ 20°C/70°F	48 hours
Recoat Time*	@ 20°C/70°F	Within 45 minutes
Solids Content	ASTM D-1259	100%
Volatile Organic Compounds (VOCs)	ASTM D-2369	0%
Theoretical coverage	N/A	1016 m ² /litre/micron (1604 ft ² /US gallon/mil)
Adhesion to steel	ASTM D-4541 (SSPC 10)	Greater than 2000 p.s.i.
Adhesion to ductile iron	ASTM D-4541	Greater than 2000 p.s.i.
Adhesion to concrete	ASTM D-4541	Greater than strength of concrete
Hardness	ASTM D-2240 Shore D	75 +/- 5
Flexibility	ASTM D-522	180° over 3" mandrel
Abrasion Resistance	ASTM D-4060 (CS-17 wheels, 1 kg weights, 1000 revolutions)	52 mg loss
Resistance to Cathodic Disbondment	CSA Z-245 (65°C, 48 hours, 20 mils)	6 mm average radius
Chemical Resistance	ASTM D-543	Excellent; see Chemical Resistance Chart
Impact Resistance	ASTM D-2794	Very Good; greater than 50 in. lbs.
Colors		Off-white, Medium Gray

*However, recoat window varies depending on the spray equipment temperature setting, the ambient conditions, product temperature/thickness, and the temperature of the substrate being coated.

NOTE: All statements, technical information and recommendations contained herein are typical of results obtained under laboratory conditions and are not intended to be used as contract specifications. For specification guidelines please contact Madison Chemical.

APPLICATION INSTRUCTIONS

CONTACT MADISON FOR DETAILED APPLICATION INSTRUCTIONS.

A. SURFACE PREPARATION

- 1) Ensure that surface is clean, dry, and uncontaminated. Proceed only if the substrate temperature is more than 3°C(5°F) above the dew point temperature during surface preparation and coating application.
- 2) Abrasive blast clean with an angular media (sand, slag, steel grit; G40 or coarser). DO NOT USE steel shot or non-angular media.
For **steel** surfaces, blast to a Near White Blast (SSPC-SP10; NACE 2; SA 2.5):
 - minimum 3.0 mil (75 microns) profile for immersion;
 - minimum 2.5 mil (65 microns) profile for buried;
 - minimum 2.0 mil (50 microns) profile for atmospheric service.For **concrete** surfaces, abrasive blast to remove any laitance. A primer or rendering material may be required to fill in any visible holes or cracks in the concrete surface.
- 3) See Madison Application Instructions for details.

B. APPLICATION OF COATING

- 1) Roll or agitate individual components thoroughly before use to disperse pigments and assure homogeneity. Do not thin. Do not mix "A" and "B" together.
- 2) Spray-apply using a plural component, 1:1 mix ratio, heated airless spray unit.
- 3) Unlimited film thickness can be obtained in one continuous coating operation, using one of several techniques. Typical applied thickness is 20 mils (500 microns) as per SSPC PA2. Contact Madison for detailed instructions.
- 4) A second coat may be applied over the first, so long as it is applied within the recoat window. Otherwise, roughening of the surface will be necessary to ensure good intercoat adhesion.
- 5) Allow coating to cure completely before putting structure into service. Follow decontamination procedure to remove any dirt and debris.
- 6) See Madison Application Instructions for details.

C. CLEAN-UP AND STORAGE

- 1) This material will react with humidity and moisture. Keep containers tightly sealed and store upside down. For clean-up, use Madison VR-1 Viscosity Reducer, M.E.K., or a 50:50 blend of M.E.K. and Xylol. Other solvents may react with product.
- 2) Store between 10°C(50°F) and 27°C(80°F). DO NOT FREEZE. Use product within 6 months of receiving.

HEALTH AND SAFETY

CorroCote II PW is intended for industrial use only. It contains no monomeric isocyanates but may nevertheless cause respiratory distress in some people. Provide ample ventilation. Wear a fresh air respirator when using in confined areas or when spraying. Wear rubber gloves, safety goggles and protective clothing. If swallowed, DO NOT induce vomiting as this will cause additional throat irritation; contact physician. If splashed on skin, remove immediately with rubbing alcohol and then wash with soap and water. If splashed in eyes, wash liberally with clean water and contact physician; temporary irritation of eyes may last several days. Contains no known or suspected carcinogens or mutagens. See MSDS for more information. The finished product is completely inert and harmless.

LIMITED TWO YEAR WARRANTY

Madison will replace any product which, in service for which it is suitable, fails to meet specifications within two years of sale and which is proven to be defective when applied according to instructions by a Madison Approved Applicator or Certified OEM Applicator. Madison accepts no responsibility or liability for any other loss, claim, damage, injury or expense, direct or consequential, in contract or negligence. This product replacement warranty is in lieu of any other right, warranty, guarantee or condition, statutory or otherwise, expressed or implied, whether as to fitness for a particular purpose or as to merchantable quality or otherwise.

The information contained herein is believed to be accurate as of the date of publication. Madison reserves the right to change product specifications without notice.

f:\data\it\library\30tds.inf\cc pw tds ver 03 2008 01 15

